



## LEMEX INTERNATIONAL AG

Bahnhofstrasse 13  
CH 6340 Baar  
Switzerland  
Tel. +41 41 760 88 68  
Fax +41 41 760 88 78  
martineichn@lemex.ch

### Crushed Sulphur

#### Technical data:

Test	Method	Result
Appearance - color		brown - yellow
Purity (on dry basis) (WT%) greater than or equal to	GOST 127.1-93	99.20
Ash content (WT%) less than or equal to	GOST 127.1-93	0.4
Moisture less than or equal to	GOST 127.1-93	1.0
Organic substances less than or equal to	GOST 127.1-93	0.5
Acidity (as H <sub>2</sub> SO <sub>4</sub> ) less than or equal to	GOST 127.1-93	0.02
As less than or equal to	GOST 127.1-93	0.03
Se less than or equal to	GOST 127.1-93	0.04
Not radioactive		
Size:		Small lumps
Particle size		2 mm to 200 mm
Size distribution	2 - 50 mm	50%
	51 -100 mm	35%
	101 – 200 mm	25 %